

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09B 67/50, 67/04, C09D 11/02 // C09B 67/12, 67/16, 67/18		A1	(11) International Publication Number: WO 99/54410
			(43) International Publication Date: 28 October 1999 (28.10.99)
(21) International Application Number: PCT/EP99/02619		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 19 April 1999 (19.04.99)		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(30) Priority Data: 9808169.8 20 April 1998 (20.04.98) GB			
(71) Applicant: CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).			
(72) Inventors: MATHERS, Richard, Ernest; 23 Craighurn Crescent, Houston, Renfrewshire PA6 7NE (GB). KEIRS, David; 11 Stanley Drive, Paisley, Renfrewshire PA2 6HE (GB). DYKES, Kenneth, Grant; 28 Newford Grove, Clarkston, Glasgow G76 8QZ (GB). HEALY, Thomas; 37 Weavers Road, Paisley PA2 9DP (GB).			
(54) Title: PRODUCTION PROCESS OF COPPER PHTHALOCYANINE IN THE BETA MODIFICATION			
(57) Abstract			
<p>The present invention provides a process for the production of pigmentary copper phthalocyanine in the beta crystalline phase comprising: a) dry or aqueous milling of crude copper phthalocyanine in combination with a natural or chemically modified resin and, optionally, a grinding auxiliary followed by; b) isolation of the milled mass followed by; c) conditioning treatment of the milled mass.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

WO 99/54410

- 1 -

PCT/EP99/02619

PRODUCTION PROCESS OF COPPER PHTHALOCYANINE IN THE BETA MODIFICATION

Technical Field

The present invention relates to a process for the production of copper phthalocyanine pigment compositions which are useful in the coloration of surface coatings, especially oil ink formulations used in printing.

The production of copper phthalocyanine pigments via milling of crude copper phthalocaynine in the presence of grinding auxiliaries such as organic/inorganic salts followed by either a separate solvent treatment with partially water miscible solvents, as detailed in British Patent number GB1140836, or, a separate aqueous emulsion treatment of the milled mass with liquid amines in the presence of surfactants such as an alkali metal salt of wood rosin, as detailed in US Patent number US5449774, are known. Where the solvent treatment step involves the use of polar aliphatic solvents, as disclosed in GB1140836, the initial dry (substantially liquid free) milling step requires a high proportion of the grinding auxiliary such as organic/inorganic salts, typically 2 parts grinding auxiliary to 1 part of crude copper phthalocyanine.

Surprisingly we have now found that the milling of crude copper phthalocyanine in combination with natural or chemically-modified resins followed by a separate solvent conditioning or aqueous emulsion conditioning treatment leads to copper phthalocyanine compositions which exhibit superior pigmentary properties versus pigment compositions produced according to the method of GB1140836 or US5449774. In particular, the copper phthalocyanine compositions of the present invention demonstrate improved colour strength; gloss; and dispersion properties, especially when formulated into oil ink formulations. Furthermore, the process according to the present invention allows for a significant reduction, versus the process of GB 1140836, in the amount of traditional grinding auxiliary material, such as organic/inorganic salts, when the subsequent conditioning step involves solvent. The use of the process of the present invention provides a more efficient and effective throughput of pigmentary material versus the process disclosed in GB1140836.

WO 99/54410

PCT/EP99/02619

Summary of the invention

- 2 -

Accordingly, the present invention provides a process for the production of pigmentary copper phthalocyanine in the beta crystalline phase comprising:

- a) dry or aqueous milling of crude copper phthalocyanine in combination with a natural or chemically modified resin and, optionally, a grinding auxiliary followed by ;
- b) isolation of the milled mass followed by ;
- c) conditioning treatment of the milled mass.

Description

As an essential step in the process according to the present invention the crude copper phthalocyanine is co-milled with a natural or chemically modified resin and optionally a grinding auxiliary. Crude in respect of copper phthalocyanine, as defined herein, means of non-pigmentary size, typically more than about 10 microns..

The crude copper phthalocyanine is prepared by any of the well established processes such as reaction at elevated temperature of phthalic anhydride with urea and a copper salt in the presence of a catalytic amount of a transition metal compound such as ammonium molybdate, the reaction being carried out in a high boiling aromatic solvent such as nitrobenzene or in the absence of solvent in a "dry-bake" process. Standard processes for the production of crude copper phthalocyanine are detailed in "Phthalocyanine Compounds" by Moser and Thomas, Reinhold Publishing Corporation 1963 the disclosures of which are incorporated herein by reference.

Resins suitable for use in the process of the present invention include rosin, the principal component of which is abietic acid; chemically modified rosins such as hydrogenated, dehydrogenated or disproportionated rosin; dimerised or polymerised rosin; partially esterified rosin; non-esterified or partially esterified maleic- or phenolic-modified rosin and rosin or rosin derivatives polymerised with substances like formaldehyde and mixtures thereof. Preferred resins for use herein include such commercially available materials as Staybelite® resin (hydrogenated rosin) available from Hercules (United States), Recoldis A resin®

WO 99/54410

- 3 -

PCT/EP99/02619

(disproportionated rosin) as distributed in Britain by Langley Smith (Britain), and Dymex® resin (dimerised rosin) available from Hercules (United States). In the milling stage, the natural or chemically-modified resin is generally present in an amount of from about 1% to about 15%, preferably from about 2% to about 5% by weight, based on the weight of crude copper phthalocyanine charged to the milling apparatus. The preferred resins in the present invention are hydrogenated rosin and disproportionated rosin.

A grinding auxiliary, as defined herein, means any material used to aid the reduction in size of copper phthalocyanine from crude to pigmentary using attrition / grinding technology. Grinding auxiliary materials suitable for use in the process of the present invention include, calcium chloride, sodium chloride, sodium sulphate, sodium formate, sodium acetate or other organic or inorganic salt, phthalimide or phthalic anhydride and mixtures thereof. The preferred grinding auxiliaries in the present invention are sodium formate, sodium chloride and sodium acetate. Where the milling is effected by a dry milling technique, the grinding auxiliary is present in an amount of from about 2% to about 15 %, preferably from about 6% to about 8 % by weight, based on the weight of crude copper phthalocyanine charged to the milling apparatus.

Milling, as defined herein, means a process by which the solids are subjected to attrition, grinding etc. to achieve particle size reduction. Dry milling, as defined herein, means a process by which the solids are subjected to attrition, grinding etc. to achieve particle size reduction while substantially free of liquid. However as detailed later herein, a low level of solvent (or amine) may be added during the milling stage. Milling of the crude copper phthalocyanine and resin mixture of the present invention may be effected by either a dry or aqueous technique. If the milling is effected by a dry technique, suitable apparatus may be a ball mill or a vibration mill. If the milling is performed in an aqueous medium, the apparatus used is conveniently a bead mill. Where the milling is effected in an aqueous medium, there is no requirement for a grinding auxiliary.

As a second essential step in the process according to the present invention the milled mixture (of crude copper phthalocyanine, resin and optionally grinding auxiliary) is isolated. Where the milling step was essentially a dry process the milled mass may be isolated by direct discharge from the milling apparatus. Where milling was effected by an aqueous milling technique, the milled mass is isolated in powder form. However, if the conditioning of the milled mass is to be effected by

WO 99/54410

- 4 -

PCT/EP99/02619

emulsion treatment, then the milled mass which has been generated by an aqueous milling technique may optionally be isolated and used in the subsequent emulsion conditioning step in the form of a "filter cake".

As a further essential step in the process of the present invention the isolated milled mixture of crude copper phthalocyanine, resin, and optionally, grinding auxiliary is conditioned either by treatment with a solvent, an emulsion or with a carboxylic acid.

Where conditioning is effected via treatment with a solvent the milled mass is dispersed into the solvent by addition, either portion-wise or a single addition, and agitation until fully "wetted out" so that all the dry mass is in contact with solvent. An aqueous solution of the resin may be added at this stage at a level of from 0 to about 10%, preferably from about 1% to about 5% by weight of the crude copper phthalocyanine. The resultant slurry is then heated to temperatures ranging from about 50°C to the boiling point of the solvent. The solvent treatment is performed for sufficient time to allow conversion of the pigmentary copper phthalocyanine to substantially the beta crystalline modification. Such phase change can be routinely monitored using standard analytical techniques such as Infra Red Adsorption Spectroscopy. Determination of the necessary settings to determine the characteristic peaks for the α and β forms is a matter of routine experimentation. The temperature and time required to effect this change, from α to β , is dependent on the crystallising effect of the solvent e.g. some solvents, such as chloroform, are able to cause phase change at room temperature in short periods of time. After such solvent conditioning, the pigmentary form of beta copper phthalocyanine is separated from the mass by typically firstly contacting with dilute mineral acid such as hydrochloric acid or dilute base such as potassium hydroxide to aid removal of the solvent, followed by removal of solvent for instance by filtration or centrifugation. If the solvent is water miscible, water may be added at the end of the solvent conditioning step and the solvent removed by azeotropic distillation. The product may then be isolated by conventional filtration and drying technologies.

Preferred solvents for use herein are polar aliphatic solvents. Suitable solvents for use in the present process can be selected from a wide variety of chemical types and include for example, methanol, ethanol, n-propanol, isopropanol, n-butanol, iso-butanol, pentanol, or other lower alcohol ; ethyl acetate or other lower alkyl monocarboxylate ; acetone, methyl ethyl ketone, methyl isobutyl ketone or other dialkyl ketone ; 2-methoxy

WO 99/54410

- 5 -

PCT/EP99/02619

ethanol, 2-ethoxy ethanol or other lower alkoxy alkanol ; ethylene glycol, diethylene glycol or other alkylene glycol and mixtures thereof.

Preferred are also mixtures of water with lower alcohols, like methanol, ethanol, n-propanol, isopropanol, n-butanol, iso-butanol, pentanol or other lower alcohols. Preferred lower alcohols for such mixtures are n-propanol, isopropanol, n-butanol or iso-butanol, especially n-butanol or iso-butanol. Highly preferred as a lower alcohol is n-butanol. These mixtures contain preferably more than 50% by weight, especially more than 75% by weight, of water. Important mixtures are those which contain 80 to 98% by weight of water and 2 to 20% by weight of lower alcohols; especially 90 to 95% by weight of water and 5 to 10% by weight of lower alcohols.

Further preferred solvents in the present invention are those which are at least partially water miscible and capable of forming an azeotropic mixture with water. In such cases the polar aliphatic solvent may contain dissolved water in a proportion which is insufficient to cause separation into two phases. The solvent may be generally used in an amount which is 200 to 1000 %, preferably 400 to 800 % relative to the weight of the starting mass to be milled (crude copper phthalocyanine, resin and optional grinding auxiliary). Furthermore, a proportion of the solvent (typically 1-5%) which is used for the solvent treatment may optionally be incorporated at the milling stage described above

Preferred carboxylic acids for use herein include: 2-ethyl hexanoic acid, oleic acid, caproic acid, valeric acid or other C₄-C₂₀ linear or branched aliphatic carboxylic acids and mixtures thereof. The carboxylic acid may be generally used in an amount which is 200 to 1000 %, preferably 400 to 800 % relative to the weight of the starting mass to be milled (crude copper phthalocyanine, resin and optional grinding auxiliary). Furthermore, a proportion of the carboxylic acid (typically 1-5%) which is used for the conditioning treatment may optionally be incorporated at the milling stage described above

Emulsion conditioning treatment of the milled mass (either as dry powder or aqueous milled dispersion or "filter-cake") is effected by mixing with an emulsion containing liquid C₆ - C₂₀ amine in water as well as an additional amount of resin salt. Typically, the resin salt is present at an amount of from 0 to 10%, preferably from about 1% to about 5% by weight of the crude copper phthalocyanine. The liquid amine may be mono-, di-, or tri-amine and may be aliphatic or aromatic in nature. Examples of suitable amines are C₇ - C₁₆ alkyl mono amines and aliphatic diamines having the

WO 99/54410

- 6 -

PCT/EP99/02619

formula $\text{RNH.CHCH}_2\text{CH}_2\text{CH}_2\text{NH}_2$ in which R is a C_{12} - C_{16} aliphatic radical such as the tallow or coco (lauryl) radical. Aryl amines include aniline and C_1 - C_4 alkyl-substituted anilines such as o-toluidine, N,N-diethylaniline and N,N-dimethylaniline. The amount of amine used may generally be from about 2% to about 50%, preferably from about 5% to about 30% by weight, based on the weight of copper phthalocyanine contained in the milled mass. Furthermore, a proportion of the amine (typically from about 1% to about 20%) which is used in the emulsion treatment step may optionally be incorporated at the milling stage as described above. The emulsification step is aided by the generation of an alkali metal salt of the natural or chemically-modified resin by addition of sodium or potassium hydroxide. The mixing of the milled mass in the emulsion treatment is generally effected at an elevated temperature, e.g. at a temperature within the range of from 20°C to 100°C and preferably from 40°C to 70°C . and is performed for sufficient time that the pigmentary copper phthalocyanine is substantially in the beta crystalline modification.

After the emulsion treatment is complete, as assessed by the conversion from the α to β crystal form of the copper phthalocyanine, the mixture is rendered acidic preferably by lowering the pH of the mixture to below 1.5 by adding mineral acid. The effect of acidifying the mixture is twofold. Firstly, the amine used in the emulsion treatment is transformed into an amine salt which is soluble in the aqueous phase and hence capable of being removed from the final pigment by filtration/washing. Secondly, the natural or chemically-modified resin is regenerated in its free acid form. Additional standard analytical techniques such as electron microscopy may be employed to measure the particle size and assess the crystal shape at this stage. After acidification, the pigment slurry may be filtered, washed with water and dried. The copper phthalocyanine pigment obtained in the beta crystalline modification according to the present invention exhibits excellent colour strength, gloss, and dispersion level relative to analogous products whereby the incorporation of natural or chemically-modified resins takes place after the milling step. Furthermore the copper phthalocyanine pigments obtained by the "dry milling/solvent treatment" component of the present invention exhibit significantly enhanced process throughput rates due to the significant reduction in the amount of grinding auxiliary required at the dry milling stage.

The copper phthalocyanine pigment produced by the present invention is particularly suited to oil ink applications. The pigment product is also useful as a colourant in publication gravure inks, in paints and in plastics. To enhance performance in publication gravure ink, paint or plastic

WO 99/54410

- 7 -

PCT/EP99/02619

systems, up to about 20%, preferably up to about 10%, more preferably from about 1% to about 5% by weight, of an additive which may be a derivative of copper phthalocyanine may be added at any stage to the pigment product obtained according to the process of present invention. Examples of such additives include dimethylaminomethyl copper phthalocyanine or phthalimidomethyl copper phthalocyanine in which the number of substituent groups on the copper phthalocyanine molecule ranges from 1 to 4, preferably from 2 to 3 ; sulphonated copper phthalocyanine ; or amine salt of sulphonated copper phthalocyanine and mixtures thereof.

The following non-limiting Examples further illustrate the present invention.

EXAMPLE 1

Preparation of a heatset oil ink from copper phthalocyanine including hydrogenated rosin added at the conditioning treatment stage.

A mixture of 93.2g crude Copper Phthalocyanine and 6.8g sodium formate are ground in a 0.6 litre vibratom ballmill until the phase change gives an α content of between about 50% and about 75%. The α content is monitored by infra red absorption spectroscopy as detailed earlier herein. 250g of water, 15.3g of 50% potassium hydroxide solution and 40g of hydrogenated wood rosin are stirred until a solution is formed. Water is then added until the solution has a volume of 267mls. 70g of the ground Copper Phthalocyanine mixture described above is added to 200mls IPS2 (83% isopropyl alcohol and 17% water) as supplied by Charles Tennant in the UK, and 10.5g of the above mentioned hydrogenated wood rosin solution. The pigmented slurry is then stirred for about 4 hours at the reflux temperature of the solvent before the addition of 200mls water. The solvent fraction of the slurry is then removed by distillation. Following distillation, 30mls of 36% hydrochloric acid is added to the slurry. The acidified slurry is then filtered using Buchner apparatus, washed with water until the pigment is essentially free of acid and formate ions (less than about 1000 micro siemens) and the resulting β form of the pigment is then dried at about 75°C until substantially free of moisture (less than about 1% moisture).

20g of the β form of the pigment so obtained is premixed with 80g of a typical heatset oil ink varnish. 100g of the premix are three roll milled on a Buhler SDY-200 3 roll mill at 23°C for about 5 minutes.

WO 99/54410

- 8 -

PCT/EP99/02619

1st dispersion pass at 10 Bar (1000 K Pa)
2nd dispersion pass at 25 Bar (2500 K Pa)
3rd dispersion pass at 25 Bar (2500 K Pa)

Assessment of the properties of the heatset oil ink obtained is made by reducing the third pass ink (20% pigmentation) to 14% pigment with the above varnish and printing using a Prufbau[®] printing machine to give prints with differing film weights. A typical heatset oil ink, as defined herein, contains a blend of modified phenolic resin, alkyd resin, petroleum distillate and from 0 to 5% of auxiliaries. The print density for each print (at different film weight) is measured using a densitometer (such as the Gretag D19C). The gloss is measured at equal film weight using an Erichsen Mini glossmaster[®] at 60°.

EXAMPLE 2

Preparation of a heatset oil ink from copper phthalocyanine including hydrogenated rosin added at the conditioning treatment stage.

The process of Example 1 was repeated with the exception that 21.0g of the hydrogenated wood rosin solution was added instead of 10.5g.

The heatset oil ink of Example 2 was assessed as detailed for Example 1.

EXAMPLE 3

Preparation of a heatset oil ink from copper phthalocyanine including hydrogenated rosin added at the grinding stage.

A mixture of 91.0g crude Copper Phthalocyanine, 2.3g hydrogenated wood rosin and 6.7g sodium formate are ground in a ballmill until the phase change gives an α content of between about 50% and about 75%. 70g of the ground Copper Phthalocyanine mixture described above is added to 200mls IPS2 (83% isopropyl alcohol and 17% water) with 10mls of 50% potassium hydroxide solution. The pigmented slurry is then stirred for about 4 hours at reflux before the addition of 200mls water. The IPS2 fraction of the slurry is then removed by distillation. Finally 25mls of 36% hydrochloric acid is added. The acidified slurry is filtered, washed with water until the pigment is free of acid and formate ions and the beta pigment dried at 75°C.

The heatset oil ink of Example 3 was assessed as previously detailed.

WO 99/54410

- 9 -

PCT/EP99/02619

Example 3 is repeated, except using 200mls of a mixture of 93% by weight of water and 7% by weight of n-butanol instead of 200mls IPS2 (83% isopropyl alcohol and 17% water).

Example 3 is repeated, except using 200mls of a mixture of 93% by weight of water and 7% by weight of iso-butanol instead of 200mls IPS2 (83% isopropyl alcohol and 17% water).

EXAMPLE 4

Preparation of a heatset oil ink from copper phthalocyanine including hydrogenated rosin added at the conditioning treatment stage.

A mixture of 93.2g crude Copper Phthalocyanine and 6.8g sodium formate are ground in a ballmill until the phase change gives an α content between 50 - 75%. 111g water at 55°C, 11.1g 50% potassium hydroxide solution, 2.5g hydrogenated wood rosin and 6.1g N, N-diethylaniline are stirred on a high speed mixer until an emulsion is obtained. The presence of an emulsion is determined by visual analysis. 55g of the ground Copper Phthalocyanine mixture described above and 150g of water at 55°C are then added to the emulsion. The pigmented emulsion is stirred for about 4 hours at about 55°C. A solution of 3.6g of calcium chloride in 42mls of water is then added, the slurry being stirred for about a further 30 minutes. Finally 30mls of 36% hydrochloric acid is added. The acidified slurry is filtered, washed with water until the pigment is free of acid and formate ions and the β pigment dried at about 75°C.

The heatset oil ink of Example 4 was assessed as previously stated.

EXAMPLE 5

Preparation of a heatset oil ink from copper phthalocyanine including hydrogenated rosin added at the grinding stage.

A mixture of 91.0g crude Copper Phthalocyanine, 2.3g hydrogenated wood rosin and 6.7g sodium formate are ground in a ballmill until the phase change gives an α content of between about 50% and about 75%. 111g water at 55°C, 11.1g 50% potassium hydroxide solution, 1.3g hydrogenated wood rosin and 6.1g N, N-diethylaniline are stirred on a high speed mixer until an emulsion is obtained. 55g of the ground Copper Phthalocyanine mixture described above and 150g of water at 55°C are added to the emulsion. The pigmented emulsion is stirred for about 4

WO 99/54410

- 10 -

PCT/EP99/02619

hours at about 55°C. A solution of 3.6g of calcium chloride in 42mls of water is then added, the slurry being stirred for about a further 30 minutes. Finally 30mls of 36% hydrochloric acid is added. The acidified slurry is filtered, washed with water until the pigment is free of acid and formate ions and the β pigment dried at 75°C.

The heatset oil ink of Example 5 was assessed as previously stated.

EXAMPLE 6

Preparation of a heatset oil ink from copper phthalocyanine including hydrogenated rosin added at the grinding stage.

A mixture of 91.0g crude Copper Phthalocyanine, 2.3g hydrogenated wood rosin and 6.7g sodium formate are ground in a ballmill until the phase change gives an α content of between about 50% and about 75%. 111g water at 55°C, 11.1g 50% potassium hydroxide solution, 3.9g hydrogenated wood rosin and 6.1g N, N-diethylaniline are stirred on a high speed mixer until an emulsion is obtained. 55g of the ground Copper Phthalocyanine mixture described above and 150g of water at 55°C are added to the emulsion. The pigmented emulsion is stirred for about 4 hours at about 55°C. A solution of 3.6g of calcium chloride in 42mls of water is then added, the slurry being stirred for about a further 30 minutes. Finally 30mls of 36% hydrochloric acid is added. The acidified slurry is filtered, washed with water until the pigment is free of acid and formate ions and the beta pigment dried at 75°C.

The heatset oil ink of Example 6 was assessed as previously stated.

EXAMPLE 7

Preparation of a heatset oil ink from copper phthalocyanine including gum rosin added at the conditioning treatment stage.

A mixture of 91.2g crude Copper Phthalocyanine and 8.8g calcium chloride are ground in a ballmill until the phase change gives an α content between about 50% and about 75%. 64.3g of the ground Copper Phthalocyanine mixture described above and 5.7g of gum rosin are added to 500mls of methyl isobutyl ketone (MIBK) with 50mls of 50% potassium hydroxide solution. The pigmented slurry is then stirred on a high speed mixer for about 15 minutes at about 80°C. The high speed mixer was then replaced with a paddle stirrer and the pigmented slurry stirred for 2 hours at 80°C. Finally 30mls of 36% hydrochloric acid is

WO 99/54410

- 11 -

PCT/EP99/02619

added. The acidified slurry is filtered, washed with acetone until the pigment is free of MIBK and the beta pigment dried at room temperature.

The heatset oil ink of Example 7 was assessed as previously stated.

EXAMPLE 8

Preparation of a heatset oil ink from copper phthalocyanine including gum rosin added at the grinding stage.

A mixture of 83.8g crude Copper Phthalocyanine, 8.1g gum rosin and 8.1g calcium chloride are ground in a ballmill until the phase change gives an α content of between about 50% and about 75%. 70g of the ground Copper Phthalocyanine mixture described above is added to 500mls of methyl isobutyl ketone (MIBK) with 50mls of 50% potassium hydroxide solution. The pigmented slurry is then stirred on a high speed mixer for about 15 minutes at about 80°C. The high speed mixer was then replaced with a paddle stirrer and the pigmented slurry stirred for about 2 hours at about 80°C. Finally 30mls of 36% hydrochloric acid is added. The acidified slurry is filtered, washed with acetone until the pigment is free of MIBK and the beta pigment dried at room temperature.

The heatset oil ink of Example 8 was assessed as previously stated.

EXAMPLE 9

Preparation of a liquid ink from copper phthalocyanine including hydrogenated rosin added at the conditioning treatment stage.

The pigment was prepared as per Example 1 with the incorporation of 3% w/w on copper phthalocyanine of dimethylaminomethyl copper phthalocyanine during the final processing stage.

15g of the dried product are mixed with 80g of phenolic varnish and 5g of toluene for about 15 minutes at about 60°C and 4000rpm using a high speed mixer such as the Dispermat FTS. 320g of 2mm glass beads are added and the mixture dispersed at 2000rpm for 30 minutes. The millbase was then reduced to 8.45% using toluene and the liquid ink of Example 9 was assessed as previously described.

EXAMPLE 10

Preparation of a liquid ink from copper phthalocyanine including hydrogenated rosin added at the grinding stage.

WO 99/54410

- 12 -

PCT/EP99/02619

The pigment was prepared as per Example 3 with the incorporation of 3% w/w on copper phthalocyanine of dimethylaminomethyl copper phthalocyanine during the final processing stage. 15g of the dried product are mixed with 80g of phenolic varnish and 5g of toluene for about 15 minutes at about 60°C and 4000rpm using a Dispermat FTS high speed stirrer. 320g of 2mm glass beads are added and the mixture dispersed at 2000rpm for 30 minutes. The millbase was then reduced to 8.45% using toluene and the liquid ink of Example 10 was assessed as previously described.

EXAMPLE 11

Preparation of a heatset oil ink from copper phthalocyanine including disproportionated rosin added at the conditioning treatment stage.

A mixture of 93.2g crude Copper Phthalocyanine and 6.8g sodium formate are ground in a ballmill until the phase change gives an α content of between about 50% and about 75%. 48.8g of the ground Copper Phthalocyanine mixture described above is added to 1.2g of disproportionated rosin and 300g of 2-ethyl hexanoic acid (2-EHA). The pigmented slurry is then stirred on a high speed mixer for about 1 hour at about 80°C. The high speed mixer was then replaced with a paddle stirrer and the pigmented slurry stirred for about 2 hours at about 80°C. Finally 219g of 33% ammonium hydroxide solution is added. The slurry is filtered, washed with acetone until the pigment is free of 2-EHA and the beta pigment dried at room temperature.

The heatset oil ink of Example 11 was assessed as per Example 1.

EXAMPLE 12

Preparation of a heatset oil ink from copper phthalocyanine including disproportionated rosin added at the grinding stage.

A mixture of 91.0g crude Copper Phthalocyanine, 2.3g disproportionated rosin and 6.7g sodium formate are ground in a ballmill until the phase change gives an α content of between about 50% and about 75%. 50.0g of the ground Copper Phthalocyanine mixture described above is added to 300g of 2-ethyl hexanoic acid (2-EHA). The pigmented slurry is then stirred on a high speed mixer for about 1 hour at about 80°C. The high speed mixer was then replaced with a paddle stirrer and the pigmented slurry stirred for about 2 hours at about 80°C. Finally 219g of 33% ammonium hydroxide solution is added. The slurry is filtered, washed

WO 99/54410

- 13 -

PCT/EP99/02619

with acetone until the pigment is free of 2-EHA and the beta pigment dried at room temperature.

The heatset oil ink of Example 12 was assessed as per Example 1.

In the tests of Examples 1 - 12, dispersion is determined visually and graded by comparison with the standard levels of the control, + indicating one grade better than standard, ++ two grades better than standard, +++ three grades better than standard etc., and = indicating similar to standard. Colour strength and gloss are determined visually and instrumentally. Colour strength as defined herein, means, optical density/ink film weight, wherein the density is measured using a densitometer.

TABLE 1

	Example 1	Example 2	Example 3
Dispersion Microscope	control	=	+++
Spotting and filtration (1st pass)	control	=	+++
Strength	control	=	+10
Gloss	control	=	++

Table 1 shows the advantages in an oil ink system when the rosin is added at the grinding stage before the conditioning treatment using a solvent.

TABLE 2

	Example 4	Example 5	Example 6
Dispersion Microscope	control	=	=
Spotting and filtration (1st pass)	control	=	=
Strength	control	+10	+5
Gloss	control	++	++

Table 2 shows the advantages in an oil ink system when the rosin is added at the grinding stage before the conditioning treatment using a liquid amine in the presence of a surfactant.

WO 99/54410

- 14 -

PCT/EP99/02619

TABLE 3

	Example 7	Example 8
Dispersion Microscope	control	=
Spotting and filtration (1st pass)	control	+
Strength	control	+8
Gloss	control	+

Table 3 shows the advantages in an oil ink system when the rosin is added at the grinding stage before the conditioning treatment using a solvent.

TABLE 4

	Example 9	Example 10
Dispersion Microscope	control	++
Strength (coated)	control	+8
Gloss (coated)	control	+++
Strength (uncoated)	control	+5

Table 4 shows the advantages in a liquid ink system when the rosin is added at the grinding stage before the conditioning treatment with a solvent.

TABLE 5

	Example 11	Example 12
Dispersion Microscope	control	++
Spotting and filtration (1st pass)	control	+
Strength	control	+4
Gloss	control	++

Table 5 shows the advantages in an oil ink system when the rosin is added at the grinding stage before the conditioning treatment using a carboxylic acid.

WO 99/54410

- 15 -

PCT/EP99/02619

Claims

1. A process for the production of pigmentary copper phthalocyanine in the beta crystalline phase comprising:
 - a) dry or aqueous milling of crude copper phthalocyanine in combination with a natural or chemically modified resin and, optionally, a grinding auxiliary followed by ;
 - b) isolation of the milled mass followed by ;
 - c) conditioning treatment of the milled mass.
2. A process according to Claim 1 wherein the natural or chemically modified resin is selected from: rosin; chemically modified rosins such as hydrogenated, dehydrogenated or disproportionated rosin; dimerised or polymerised rosin; partially esterified rosin; non-esterified or partially esterified maleic- or phenolic-modified rosin and rosin or rosin derivatives polymerised with substances such as formaldehyde and mixtures thereof.
3. A process according to Claim 1 or 2 wherein the resin is a hydrogenated rosin, a disproportionated rosin, a dimerised rosin or mixtures thereof.
4. A process according to any of Claims 1 to 3 wherein the resin is present at a level of from about 1% to about 15%, preferably from about 2% to about 5% by weight, relative to the level of crude copper phthalocyanine employed.
5. A process according to any of Claims 1 to 4 wherein the grinding auxiliary is selected from: calcium chloride, sodium chloride, sodium sulphate, sodium formate, sodium acetate or other organic or inorganic salt, phthalimide or phthalic anhydride and mixtures thereof.
6. A process according to any of Claims 1 to 5 wherein the grinding auxiliary is selected from sodium formate, sodium chloride, sodium acetate and mixtures thereof.
7. A process according to any of Claims 1 to 6 wherein the grinding auxiliary is present at a level of from about 2% to about 15%,

WO 99/54410

- 16 -

PCT/EP99/02619

preferably from about 6% to about 8% by weight, relative to the level of crude copper phthalocyanine employed.

8. A process according to any of Claims 1 to 7 wherein the conditioning treatment of the milled mass is effected via treatment with solvent, an emulsion or a carboxylic acid.
9. A process according to any of Claims 1 to 8 wherein the conditioning treatment is effected with a solvent selected from: methanol, ethanol, n-propanol, isopropanol, n-butanol, iso-butanol, pentanol, or other lower alcohol ; ethyl acetate or other lower alkyl monocarboxylate ; acetone, methyl ethyl ketone, methyl isobutyl ketone or other dialkyl ketone ; 2-methoxy ethanol, 2-ethoxy ethanol or other lower alkoxy alkanol ; ethylene glycol, diethylene glycol or other alkylene and mixtures thereof ; or a mixture of water and methanol, ethanol, n-propanol, isopropanol, n-butanol, iso-butanol, pentanol or other lower alcohol.
10. A process according to any of Claims 1 to 8 wherein the carboxylic acid is selected from 2-ethyl hexanoic acid, oleic acid, caproic acid, valeric acid or other C₄-C₂₀ linear or branched aliphatic carboxylic acid and mixtures thereof.
11. A process according to any of Claims 1 to 10 wherein the conditioning solvent or carboxylic acid is present at a level of from about 200% to about 1000%, preferably from about 400% to about 800% by weight, relative to the weight of the milled mass.
12. A process according to any of Claims 1 to 8 wherein the conditioning emulsion contains a liquid C₆ - C₂₀ amine selected from: aliphatic or aromatic mono-, di-, or tri-amines, such as C₇ - C₁₆ alkyl mono amines and aliphatic diamines having the formula RNH.CHCH₂CH₂CH₂NH₂ in which R is a C₁₂ - C₁₆ aliphatic radical such as the tallow or coco (lauryl) radical and aryl amines such as aniline and C₁ - C₄ alkyl-substituted anilines such as o-toluidine, N,N-diethylaniline and N,N-dimethylaniline and mixtures thereof.
13. A process according to Claim 12 wherein the liquid amine is present at a level of from about 2% to about 50%, preferably from about 5% to about 30% by weight, based on the weight of copper phthalocyanine contained in the milled mass.

WO 99/54410

- 17 -

PCT/EP99/02619

14. A process according to Claim 1 for the production of pigmentary copper phthalocyanine comprising:
 - a) dry milling of crude copper phthalocyanine in combination with hydrogenated wood rosin and sodium formate or sodium chloride or sodium acetate and mixtures thereof followed by;
 - b) isolation of the milled mass by direct discharge from the milling apparatus, followed by;
 - c) conditioning treatment of the milled mass by dispersion of the milled mass into a solvent, followed by;
 - d) heat treatment to convert the copper phthalocyanine from α to β form, followed by;
 - e) treatment of the β form copper phthalocyanine mixture with dilute mineral acid and removal of the solvent and isolation of the β form copper phthalocyanine product by filtration and drying.
15. A process according to Claim 14 wherein the conditioning treatment is effected via treatment with an emulsion.
16. A process according the Claim 1 for the production of pigmentary copper phthalocyanine in the beta crystalline phase comprising:
 - a) aqueous milling of crude copper phthalocyanine in combination with a natural or chemically modified resin followed by ;
 - b) isolation of the milled mass followed by ;
 - c) conditioning treatment of the milled mass.
17. A process according to Claim 16 wherein the milled mass is isolated in powder form.
18. A process according to Claim 16 wherein the milled mass is isolated in the form of a "filter-cake" and wherein the conditioning treatment is an emulsion treatment.

WO 99/54410

- 18 -

PCT/EP99/02619

19. β form copper phthalocyanine product obtained by the process of any of Claims 1 to 18.
20. Use of the β form copper phthalocyanine product obtained by the process of any of Claims 1 to 18 for the preparation of oil inks; grauve inks, paints and plastics.
21. A method of preparation of a heatset oil ink using the β form copper phthalocyanine product obtained by the process of any of Claims 1 to 18 substantially as described in any of Examples 1 to 8 and 11 and 12 as detailed herein.
22. A method of preparation of a liquid ink using the β form copper phthalocyanine product obtained by the process of any of Claims 1 to 18 substantially as described in Examples 9 or 10 as detailed herein.

INTERNATIONAL SEARCH REPORT

 Inter. Appl. Application No
 PCT/EP 99/02619

A. CLASSIFICATION OF SUBJECT MATTER

 IPC 6 C09B67/50 C09B67/04 C09D11/02 //C09B67/12, C09B67/16,
 C09B67/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 452 258 A (CIBA GEIGY AG) 16 October 1991 (1991-10-16) abstract; examples & US 5 449 774 A cited in the application ----	1-22
Y	FR 1 497 687 A (ICI) 4 January 1968 (1968-01-04) page 3, right-hand column, last paragraph - page 4, left-hand column, paragraph 1; examples 5,16 ----	1-22
A	EP 0 803 545 A (TOYO INK MFG CO) 29 October 1997 (1997-10-29) column 4, line 26 - line 33; claims 8,9; examples ----- -/--	1-22

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

18 August 1999

Date of mailing of the international search report

31/08/1999

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Dauksch, H

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02619

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 392 334 A (BASF AG) 17 October 1990 (1990-10-17) abstract; examples ----	1-22
A	EP 0 819 740 A (TOYO INK MFG CO) 21 January 1998 (1998-01-21) abstract; examples ----	1-22
A	EP 0 808 878 A (TOYO INK MFG CO) 26 November 1997 (1997-11-26) abstract; example 9 ----	1-22
A	EP 0 780 446 A (CIBA GEIGY AG) 25 June 1997 (1997-06-25) the whole document ----	1-8, 10
A	FR 1 512 124 A (J. R. GEIGY S.A.) 18 April 1968 (1968-04-18) the whole document & GB 1 512 124 A cited in the application ----	1-9
A	EP 0 774 494 A (CIBA GEIGY) 21 May 1997 (1997-05-21) abstract; examples -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Jnal Application No

PCT/EP 99/02619

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0452258 A	16-10-1991	DE 59107955 D	01-08-1996
		DK 452258 T	29-07-1996
		ES 2089171 T	01-10-1996
		JP 4225070 A	14-08-1992
		KR 150222 B	01-10-1998
		US 5449774 A	12-09-1995
FR 1497687 A	04-01-1968	BE 687017 A	16-03-1967
		CH 522716 A	15-05-1972
		DE 1619588 A	19-08-1971
		GB 1149898 A	
		NL 6613146 A	20-03-1967
		US 3437503 A	08-04-1969
EP 0803545 A	29-10-1997	JP 9291223 A	11-11-1997
		CA 2203611 A	26-10-1997
		CN 1174862 A	04-03-1998
		US 5772750 A	30-06-1998
EP 0392334 A	17-10-1990	DE 3911476 A	11-10-1990
		CA 2013064 A	08-10-1990
		DE 59009406 D	24-08-1995
		DK 392334 T	04-09-1995
		JP 2294365 A	05-12-1990
EP 0819740 A	21-01-1998	JP 9272833 A	21-10-1997
		CA 2217231 A	07-08-1997
		WO 9728224 A	07-08-1997
EP 0808878 A	26-11-1997	JP 9291221 A	11-11-1997
		CA 2203610 A	26-10-1997
		CN 1170738 A	21-01-1998
		US 5776237 A	07-07-1998
EP 0780446 A	25-06-1997	AU 7542896 A	26-06-1997
		BR 9606128 A	03-11-1998
		CA 2193605 A	24-06-1997
		CZ 9603807 A	13-05-1998
		JP 9194751 A	29-07-1997
		US 5776238 A	07-07-1998
FR 1512124 A	18-04-1968	CH 478213 A	15-09-1969
		DE 1619568 A	30-07-1970
		DK 118908 B	19-10-1970
		GB 1140836 A	
		JP 51001732 B	20-01-1976
		US 3523030 A	04-08-1970
EP 0774494 A	21-05-1997	AU 7174196 A	22-05-1997
		BR 9605576 A	18-08-1998
		CA 2190327 A	17-05-1997
		CZ 9603361 A	13-05-1998
		JP 9188845 A	22-07-1997
		NO 964867 A	20-05-1997
		SG 43442 A	17-10-1997